



DUFLEX LIMITED
NEWBOLD DRIVE
CASTLE DONINGTON
DERBY DE74 2QX
ENGLAND
TEL: 01332 810811
FAX: 01332 810657
WEBSITE: www.duflex.co.uk

FLAMMABILITY TO FMVSS 302 (BS AU 169)

Batch N°: A5 329 03 Thickness: 3.0 mm
Date Produced: 8.1.03 Date Tested: 15.1.03 Formula: F254

RESULTS

Direction of manufacture


| Sample N° | Burning Time (seconds) | Burn Length (mm) | Burning Rate (mm/min) |
|-----------|------------------------|------------------|-----------------------|
| 1 | 0 | 0 | Self Extinguishing |
| 2 | 0 | 0 | Self Extinguishing |
| 3 | 0 | 0 | Self Extinguishing |
| Average | | | Self Extinguishing |

Right angle to manufacture

| Sample N° | Burning Time (seconds) | Burn Length (mm) | Burning Rate (mm/min) |
|-----------|------------------------|------------------|-----------------------|
| 1 | 0 | 0 | Self Extinguishing |
| 2 | 0 | 0 | Self Extinguishing |
| 3 | 0 | 0 | Self Extinguishing |
| Average | | | Self Extinguishing |

COMMENTS

All samples extinguished before reaching the first gauge mark.

Signed: 

Date: 15.1.03

David Booth
Quality and Safety Manager

REGISTERED OFFICE: DUFLEX LIMITED
NEWBOLD DRIVE CASTLE DONINGTON DERBY DE74 2QX
REGISTERED NUMBER: 2417720



Certificate No. FM 20323